











Grey 30x60 (12"x24")

TECHNICAL CHARACTERISTICS NUTREND	VALUES	REQUIRED STANDARDS UNI EN 14411 G
 SIZES UNI EN ISO 10545-02	ACCORDING	<ul style="list-style-type: none"> • Length and width ± 0,6 % max • Thickness ± 5 % max • Linearity ± 0,5 % max • Wedging ± 0,6 % max • Warpage ± 0,5 % max
 WATER ABSORPTION UNI EN ISO 10545-03	0,2%	≤ 0,5%
 FLEXURAL STRENGTH UNI EN ISO 10545-04	ACCORDING	≥ 35 N/mm ²
 DEEP ABRASION RESISTANCE UNI EN ISO 10545-06	ACCORDING	≤ 175 mm ³
 THERMAL SHOCK RESISTANCE UNI EN ISO 10545-09	RESISTANT	NO SAMPLE MUST SHOW VISIBLE DEFECTS
 FROST RESISTANCE UNI EN ISO 10545-12	FROST-PROOF	RESISTANT
 CHEMICAL RESISTANCE* UNI EN ISO 10545-13	RESISTANT	RESISTANT
 STAIN RESISTANCE UNI EN ISO 10545-14	ACCORDING	UGL TEST METHOD AVAILABLE
 DETERMINATION OF STATIC COEFFICIENT OF FRICTION ASTM C 1028	Dry 0,71 Wet 0,68	U ≥ 0,6
 DETERMINATION OF DYNAMIC COEFFICIENT OF FRICTION BOT3000	0,60	> 0,42

*Chemical products for household use and swimming pool additives















NuTrend



Black 30x60 (12"x24")



White 30x60 (12"x24")

				NuTrend
Beige 30x60 (12"x24") R	White 30x60 (12"x24") R	Grey 30x60 (12"x24") R	Black 30x60 (12"x24") R	
				
Mosaic Beige 3,75x3,75 (1,5"x1,5") 30x30 (12"x12") sheet	Mosaic White 3,75x3,75 (1,5"x1,5") 30x30 (12"x12") sheet	Mosaic Grey 3,75x3,75 (1,5"x1,5") 30x30 (12"x12") sheet	Mosaic Black 3,75x3,75 (1,5"x1,5") 30x30 (12"x12") sheet	
				
Bullnose Beige 10x60 (4"x24")	Bullnose White 10x60 (4"x24")	Bullnose Grey 10x60 (4"x24")	Bullnose Black 10x60 (4"x24")	



Beige 30x60 (12"x24")